



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

July 17, 2017

MARLEN TEXTILES  
500 Orchard Street  
New Haven, MO 63068

Reference: Laboratory Test Report  
Lab Identification No. 26046  
Invoice No. 57205

Dear Sir or Madam:

One (1) fabric sample, identified as **TOP NOTCH FR**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 2, Large Scale)". The results are as follows:

**TEST RESULTS - FOLDS**

<u>Specimen Number</u>	<u>After Flame (seconds)</u>	<u>Residual Flame (seconds)</u>	<u>Char Length (inches)</u>
1	0.0	0.0	13.0
2	0.0	0.0	12.0
3	0.0	0.0	12.0
4	0.0	0.0	11.0

The fabric sample submitted **meets** the minimum requirements of the above standard. The length of char on the individual folded specimens shall not exceed 41.3 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

